



TEST REPORT

Disposable Microfiber Mops

Test item: Air-borne Particle
Report no.: 240144132
Test date: 30.05.2024
Issue date: 06.06.2024

Disposable Microfiber Mops 40 pcs.



12*40 cm

• 1010002081

12*60 cm

• 1010002082

20*60 cm

• 1010002083

For test result please see next page



TEST RESULT

Disposable Microfiber Mops

Lint and other particles generation in the dry state
(ISO 9073-10:2003, Size of particles counted: 0.5~25µm)

Total lintning:	
Average	362620

Coefficient of linting:	
Average	5.6

Air-borne Particle Test

Test method : D.G Method (apply to ISO 9073-10)/ Particle counter: Gelbo flex tester

1. Preparation of the particle generator and particle counter in the Clean Air bench.
2. Attachment of the test sample to the particle generator.
3. Operation of the particle generator for 30 seconds. Repeat this process 3 times.
4. Counting of particles in the generator using the particle counter.

